

PRESCOL TEKNİK ÖZELLİKLERİ

PRESCOL - MAT

Özellikler		Birim	Tolerans														
Gramaj (Substance)	ISO 536	gsm	± 4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Kalınlık (Thickness)	ISO 534	µm	± 7%	73	81	93	102	107	111	125	134	166	195	225	246	278	353
Beyazlık (Whiteness)	CIE																
D65/10 (outdoor)	ISO 11475	index	-3	118	118	118	118	118	118	118	118	118	118	118	118	118	118
C/2° (Indoor)	ISO 11476	index	-3	102	102	102	102	102	102	102	102	102	102	102	102	102	102
Opasite (Opacity)	ISO 2471	%	-2	89,5	90,5	92,5	93,5	94,0	94,5	95,5	97,0	98,5	99,0	99,0	99,5	99,5	99,5
Görel Nemlilik (Relative Humidity)	TAPPI T-502	%	± 10	48	48	48	48	48	48	48	48	48	48	44	44	44	44
Pürüzsüzlük (Smoothness Bekk)	ISO 5627	s	-100	450	450	400	600	600	600	600	300	300	250	210	200	160	70

* Values are subject to change without notice

(Değerler, fabrika tarafından haber verilmeksizin değiştirilebilir)

PRESCOL - PARLAK

Özellikler		Birim	Tolerans														
Gramaj (Substance)	ISO 536	gsm	± 4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Kalınlık (Thickness)	ISO 534	µm	± 7%	67	74	85	92	96	100	110	120	140	163	190	206	230	293
Beyazlık (Whiteness)	CIE																
D65/10 (outdoor)	ISO 11475	index	-3	123	123	123	123	123	123	123	123	123	123	123	123	123	123
C/2° (Indoor)	ISO 11476	index	-3	105	105	105	105	105	105	105	105	105	105	105	105	105	105
Opasite (Opacity)	ISO 2471	%	-2	88,0	91,0	92,5	93,5	94,0	94,5	96,0	97,0	97,5	98,0	98,5	98,5	99,0	99,5
Kağıt Parlaklığı (Paper Gloss)	TAPPI T-480	%	± 5	75	75	76	77	77	77	77	78	78	78	78	78	78	78
Görel Nemlilik (Relative Humidity)	TAPPI T-502	%	± 10	48	48	48	48	48	48	48	48	48	48	44	44	44	44

* Values are subject to change without notice

(Değerler, fabrika tarafından haber verilmeksizin değiştirilebilir)