

SORA PRESS cream

Parameter	Standard	60	65	70	80	90	100	110	120	Tolerance
Grammage [g/m ²]	ISO 536	60	65	70	80	90	100	110	120	± 2
Spec. volume [cm ³ /g]	DIN 53105	1,23	1,20	1,20	1,20	1,20	1,18	1,18	1,18	± 0,05
Smoot.Bendtsen [ml/min]	ISO 8791-2	120	120	120	120	120	120	120	120	± 50
“a”		1,3	1,3	1,3	1,3	1,3	1,3	1,3	1,3	± 0,5
“b”		8,7	8,7	8,7	8,7	8,7	8,7	8,7	8,7	± 1
Opacity [%]	ISO 2471	89	90	91	93	95	97	98	99	± 2

Given values can be used as guide values only and can be changed without prior notice.



The mark of
responsible forestry

