

Ningbo Asia Pulp & Paper

**NINGBO FOLD**

**C1S Ivory**

Basis Weight	24"x36" 500 (lb)	Thickness		Stiffness (Taber 15°)	
		µm (±4%)	pt (±4%)	mN·m (±10%)	
g/m <sup>2</sup> ±3%				CD	MD
170 *	104	205	8.1	1.2	
190	117	245	9.6	1.7	2.9
210	129	275	10.8	2.3	3.9
220	135	290	11.4	2.6	4.4
230	141	310	12.2	3.2	7.2
250	154	340	13.4	4.1	7.7
270	166	370	14.6	5.1	8.3
300	184	415	16.3	7.1	13.2
325 *	200	460	18.1	8.5	
350	215	490	19.3	11.0	22.0
400	246	555	21.9	15.4	30.8
440 *	270	610	24.0	18.0	

Property	Unit	Value
PPS (Top)	µm	≤1.8
Moisture	%	6.0 ±1.5
Brightness (Top)	%	90 ±2
75°Gloss(Top)	%	≥45
IGT Blister(Top)	m/s	≥1.0
COBB Test(60s) (Top)	g/m <sup>2</sup>	≤50
PLY Bonding	J/m <sup>2</sup>	≥130

Test condition (ISO): temp 23±1°C, relative humidity 50±2%

Note: Shaded substances are non-regular substances which are not produced regularly.

\*Draft Specification

Date: 07 Nov 2008